

This Page Is Inserted by IFW Operations
and is not a part of the Official Record

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images may include (but are not limited to):

- BLACK BORDERS
- TEXT CUT OFF AT TOP, BOTTOM OR SIDES
- FADED TEXT
- ILLEGIBLE TEXT
- SKEWED/SLANTED IMAGES
- COLORED PHOTOS
- BLACK OR VERY BLACK AND WHITE DARK PHOTOS
- GRAY SCALE DOCUMENTS

IMAGES ARE BEST AVAILABLE COPY.

**As rescanning documents *will not* correct images,
please do not report the images to the
Image Problem Mailbox.**

- (21) Application No. 4283/74 (22) Filed 30 Jan. 1974 (19)
 (31) Convention Application No. 328 425 (32) Filed 31 Jan. 1973 in
 (33) United States of America (US)
 (44) Complete Specification published 28 July 1976
 (51) INT. CL.⁸ C08K 5/00 C08L 77/08 H01K 1/32
 (52) Index at acceptance


C3R 22C 22D1B1 22D2A1 22D2AX 22N1A C12 C29
 C33B C33X C4 C9B L1B L2CX L3A L6G
 A3H 8
 B2E 198 229 348 368 417 439 445 446 44Y 80X
 H1F 2A1B 2A1CX 2A1GX



(54) CLEAR PERFUMED POLYAMIDE RESIN AND METHOD OF
 MAKING IT

- (71) We, POLAK'S FRUTAL WORKS, INC.,
 a corporation of the State of New York,
 United States of America, of the City of
 Middletown, New York, New York 10904,
 United States of America, do hereby declare
 the invention, for which we pray that a
 patent may be granted to us, and the method
 by which it is to be performed, to be par-
 ticularly described in and by the following
 statement:—
 The present invention relates to materials
 composed of clear substantially solvent-free
 polyamide resins containing perfume oils and
 to methods of making the same. By 'solvent-
 free' we mean free from solvent other than
 the resins and perfume oils themselves.
 Polyamide resins are known which vary
 from clear to opaque and from smearable
 semisolids to very hard bodies of high ten-
 sile, compressive and impact strength.
 It has been proposed to make perfumed
 objects of soft gels containing polyamide
 resin, e.g., a clear lipstick that can be
 smeared on the lips and a clear candle that
 on burning volatilizes the perfume and adds
 fragrance to the atmosphere around it. In
 these products the polyamide is used in
 relatively small proportions as a gelling
 agent in a system which otherwise contains
 a large proportion of solvent liquid, a dye
 or pigment, and a relatively small amount of
 fragrance. The gels are soft, spreadable and
 deformable at room temperature.
 It has been discovered that a clear solid,
 i.e., relatively rigid, polyamide resin material
 containing perfume oil can be made without
 substantial amounts of added solvent by
 proper selection of the polyamide resin and
 by following certain making procedures as
 set forth hereinbelow.
 According to the present invention we pro-
 vide a clear solid thermoplastic resin ma-
 terial consisting substantially of a thermo-
 plastic polyamide resin containing perfume
 oil in an amount not exceeding 30 per cent
 by weight based on the resin plus the per-
 fume oil, and being substantially free of
 solvent, said thermoplastic polyamide resin
 being a fatty polyamide which softens within
 a range of 10 to 15°C on heating in the
 range of 100–200°C., has a sharp decrease
 in viscosity at temperatures above its soften-
 ing range and has a molecular weight within
 the range 6000 to 9000.
 The resin used in the invention must be
 optically clear at room temperature to yield
 an optically clear body containing perfume
 oil. In general the polyamide resins having
 this desired clarity and suitable physical
 properties are fatty polyamides which have
 molecular weights within the range of 6,000
 to 9,000 and are based on condensation of
 polyamines, especially diamines and tri-
 amines, with high molecular weight dicar-
 boxylic acids, especially of the type which
 result from dimerization of diunsaturated
 carboxylic acids, e.g., condensation products
 of dimerized linoleic acid and ethylene di-
 amine. They are characterized by substan-
 tial retention of their room temperature
 hardness on heating until very near the
 melting or softening temperature which is
 relatively sharp, e.g., over a range of 10–
 15°C. within the range of 100 to 200°C.,
 depending on the molecular weight, and by
 a sharp decrease in viscosity at tempera-
 tures above the melting or softening point or
 range. The optical clarity is believed to be
 due to the solubility of all of the components
 in the resin. Methods of making such resins
 are disclosed in the expired U.S. Patent
 2,379,413. In contrast, some well known
 polyamide resins of the nylon type, e.g.,
 nylon 6, which are not suitable for the pres-
 ent invention have higher molecular weights
 and are opaque, probably because the com-
 ponents of the mixtures are not mutually
 soluble.
 A clear resin suitable for use in the in-
 vention is made by reacting dimerized linoleic

acid with ethylene diamine to produce a product of the formula



in which R is a hydrocarbon group of an indeterminate configuration containing 34 carbon atoms and R¹ is $\text{—CH}_2\text{CH}_2\text{—}$ and which has the following typical properties:

Softening point (Ball and Ring)	110—115°C.
Viscosity (Brookfield)	
Poises at 150°C	30—35
Poises at 160°C	21—27
Tensile Strength (P.S.I.)	1500—2000
Color (Gardner, 40% solution)	4—7
Specific Gravity	0.97

It is clear amber in color, non-tacky at room temperature, has a relatively sharp melting point and is thermoplastic with a narrow heat seal range. It exhibits good adhesion to a variety of substrates and can be applied to substrates from solution or from a melt. Thin films show good flexibility. The resin is conveniently prepared for commercial use in diced form for supplying either batch heating vessels or molding machines. Such a resin in diced form is available commercially from General Mills, Inc., under the name Versamid 930 ("Versamid" is a registered Trade Mark). Versamid 940 is similar thereto but has slightly lower viscosity, tensile strength and elongation. Versamid 1635 also is similar thereto but has a lighter color and lower inherent color. Resins having these properties are excellently suitable for the present invention. Further description of the suitable resins is unnecessary because they are well known to those skilled in the art and have been extensively described in literature published by General Mills on Versamid polyamide resins, in text books, encyclopedias, and other technical publications.

The fragrances suitable for the present invention, sometimes called perfume oils, are complex mixtures of volatile compounds including esters, ethers, aldehydes, alcohols, unsaturated hydrocarbons, e.g., terpenes, which are well known to persons skilled in the fragrance art and need not be further identified. Their use as to type and proportion in the present invention is limited only by solubility in the resin to produce a clear product.

The process of making the clear perfumed resin materials of the invention comprises melting the resin by heating it until sufficiently molten to be stirrable and pourable. For a resin having the properties specified above this condition obtains when the temperature is within the range of 100—200°C.,

and preferably below about 160°C. The perfume oil is added to the liquid resin and blended therewith, e.g., by stirring or other mechanical agitation until a uniform mixture or blend is formed. No solvent for the resin and the perfume oil need be added at any time during the process. The mixture is cooled promptly after thorough mixing to solid condition, preferably rapidly as by quenching in cold water or by pouring onto or bringing into contact with a cold metal surface to which it is not adherent. The product obtained by this process is optically clear, has a high polished surface and a strong fragrance that faithfully represents the odor of the perfume oil, especially when the resin used has low inherent odor. These products have good optical stability and retain a substantial proportion of the fragrance for months.

The perfumed materials of the present invention may be formed into a wide variety of useful objects such as jewellery, e.g., pendant earrings, pins or brooches; decorative castings such as birds, animals, or abstract objects; coatings on various substrates, e.g., on Christmas tree ornaments and electric light bulbs such as Christmas tree lights where the heat of the lighted filament increases the volatility and rate of transfer to the atmosphere of the perfume oil from the resin coating. Such coated Christmas tree ornaments and lights can be scented with pine oil, for example, to add an aspect of reality when used on artificial Christmas trees.

The proportion of perfume oil to resin may vary from small but effective amounts of the order of a percent or so up to the maximum amount the resin can contain and still maintain optical clarity which is up to 30% by weight based on the resin plus the perfume oil. In general it is preferred to use about 12% which is an optimum value balancing the proportion of perfume oil recovered in the product against the length of time period over which the objects give off a fragrant odor.

The following specific Example illustrates the method and product of the invention.

EXAMPLE

In a vessel associated with a source of heat a quantity of diced Versamid 930 amounting to 88 parts by weight is heated to about 130°C. at which temperature the resin is a pourable and stirrable body of liquid. A quantity of a perfume oil having a floral bouquet with a woody background amounting to 12 parts by weight is stirred into the liquid resin until a uniform blend is achieved at which time the mixture is poured into standing cold water to facilitate rapid cooling and solidification to minimize loss of perfume oil. The product is clear amber solid having a highly polished surface

with a pronounced odor faithfully reproducing the fragrance of the perfume oil used in making it. The product is in the form of a solid solution which lends itself to molding under heat and pressure into objects of jewellery such as pendant earrings, to casting in molds to form decorative art objects, and to spreading as a film on substrates such as Christmas tree ornament or glass light bulbs.

Similar results are achieved using Versamid 1635 and other perfume oil fragrances.

In general it is advantageous to carry out the mixing operation in a closed vessel, preferably a pressure vessel, in order to prevent substantial loss of perfume oil by vaporization. Where the final objects are made by molding, e.g., injection molding, the perfume oil is preferably introduced directly into the resin in the feed supply line, preferably after the resin is liquified, and uniformly blended into the resin therein.

WHAT WE CLAIM IS:—

1. A clear solid thermoplastic resin material consisting substantially of a thermoplastic polyamide resin containing perfume oil in an amount not exceeding 30 per cent by weight based on the resin plus the perfume oil, and being substantially free of solvent, said thermoplastic polyamide resin being

a fatty polyamide which softens within a range of 10 to 15°C on heating in the range of 100—200°C., has a sharp decrease in viscosity at temperatures above its softening range and has a molecular weight within the range 6000 to 9000.

2. A resin material as claimed in Claim 1, in which the perfume oil is in the resin as a solid solution.

3. A resin material as claimed in Claim 1 or 2, which is part of a piece of jewellery.

4. A resin material as claimed in Claim 1 or 2, which is in the form of a decorative casting.

5. A resin material as claimed in Claim 1 or 2, which is a coating on a substrate.

6. A resin material as claimed in Claim 5, in which the substrate is in the form of an ornament.

7. A resin material as claimed in Claim 5, in which the substrate is in the form of an electric light bulb.

8. A clear polyamide resin material according to Claim 1, substantially as described with reference to the foregoing Example.

For the Applicants,
CARPMAELS & RANSFORD,
Chartered Patent Agents,
43 Bloomsbury Square,
London, WC1A 2RA.